

AQUAFIX MAGIC 2K



5L 1L

As with all wood finishing always do a test area first to safeguard against an undesirable outcome. This technical data sheet is merely a guide and not a guarantee. All products are formulated to the best of our knowledge. The information is given as a result of many years experience. This product has had extensive tests carried out.

Produced by Debal Coatings nv

Industrieweg 29 - 8800 Beveren-
Roeselare Belgium tel. +32 (0) 51 30 11 40
fax +32 (0) 51 31 26 48
ciranova@ciranova.be

PRODUCT DESCRIPTION

The new Aquafix Magic 2K is an environment-friendly, transparent finish for parquet and wooden furniture. The wood retains its initial untreated look and is very matt. The new Aquafix Magic 2K has a better chemical and mechanical resistance and dries faster. Suitable for floors submitted to high traffic use. Only for interior use. Particularly for interior where a natural finish is needed such as parquet, veneer and other wooden objects.

TECHNICAL DATA

VISCOsity	+/- 20 sec. (Din 4mm/20°C)
Solid content	+/- 32 % by weight
DENSITEIT	+/- 1,04 kg/l
Gloss	matt, < 5%
Dilution	water
POT-LIFE	2-3 hours
V.O.C.	35g/l
NMP Free	

PREPARATION

Surface: Solid wood, ingeneerd wood. Sand the surface with grain 120 – 150 and afterwards remove sanding dust.

USER TIPS

Use the AQUAFIX MAGIC 2K Ciranova as a sealer and topcoat. For oak, PH-sensible wood or wood containing resins, we advise to use AQUAFIX SEALER or TANNIN BLOCKER WL as an insulator. Mix the hardener to the product (**10% = 10/1**) and stir well. After mixing or stirring the product, the product has to rest for 15 minutes before use. Application is done by brush or roller. A short haired roller is preferred. Apply the first coat wet in wet to avoid overlap joints. When the first layer is dry, apply the second layer as the first layer. When the second layer is dry, sand with grain 150-180, remove sand dust and apply the third layer.



DRYING TIMES

Dust free: 30 minutes to 1 hour
Sandable: after 2 - 4 hours
Walkable: after 16 hours
Full cured: after 3 days

The drying is strongly depending on the applied quantity, the temperature, air humidity and the ventilation of the room. Through a higher temperature and a good ventilation, drying time is limited.

AQUAFIX MAGIC 2K



5L 1L

APPLYING QUANTITY

10 - 12 m²/lt per coat.

AFTER TREATMENT

Use Hard floor fresh Ciranova for regular maintenance.
For periodic maintenance use Hard Floor Matt polish Ciranova.
For deep cleaning of a varnished floor and to remove old polish layers, use Hard Floor Cleaner.

PRODUCT INFORMATION

18 months in well-closed and original packing.
Warehousing at +5°C – 40°C: not frost-durable.

Danger class VbF: none
Dangerclass GGV5/E: none

SPECIAL QUALITIES

Use only stainless material. After use, rinse the material directly with water. This product cannot be poured into sewerage. If a stain on the wood is needed, only use AQUACOLOR Ciranova.
Be aware of discoloration or detachment because of wood compounds like resins or tannin.

As with all wood finishing always do a test area first to safeguard against an undesirable outcome. This technical data sheet is merely a guide and not a guarantee. All products are formulated to the best of our knowledge. The information is given as a result of many years experience. This product has had extensive tests carried out.

Produced by Debal Coatings nv

Industrieweg 29 - 8800 Beveren-
Roeselare Belgium tel. +32 (0) 51 30 11 40
fax +32 (0) 51 31 26 48
ciranova@ciranova.be